

Application No.: 10/730238

Case No.: 59445US002

Amendments to the Claims:

The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

1.-13. (Canceled)

14. (Currently Amended) A method of making a crosslinked polymer comprising the steps of:

a) providing a polymer comprising first pendent groups which include a group according to the formula -SO₂Cl; and

b) crosslinking said polymer by a process that comprises removal of the -SO₂Cl group;

wherein said polymer additionally comprises second pendent groups which include a group according to the formula -SO₂X' wherein each X' is independently selected from the group consisting of F and -OH;

~~The method according to claim 7~~ wherein said method additionally comprises, after said step b), the step of:

d) converting any remaining groups according to the formula -SO₂X' to sulfonic acid groups.

15.-18. (Canceled)

19. (Currently Amended) A method of making a crosslinked polymer comprising the steps of:

a) providing a polymer comprising first pendent groups which include a group according to the formula -SO₂Cl; and

b) crosslinking said polymer by a process that comprises removal of the -SO₂Cl group;

~~The method according to claim 1~~ wherein step a) of providing a polymer comprises the steps of:

e) providing a polymer comprising pendent groups which include a group according to the formula -SO₂F; and

Application No.: 10/730238

Case No.: 59445US002

- f) converting at least a portion of said $\text{-SO}_2\text{F}$ groups to $\text{-SO}_2\text{Cl}$.

20. (Currently Amended) A method of making a crosslinked polymer comprising the steps of:

- a) providing a polymer comprising first pendent groups which include a group according to the formula $\text{-SO}_2\text{Cl}$; and

- b) crosslinking said polymer by a process that comprises removal of the $\text{-SO}_2\text{Cl}$

group;

~~The method according to claim 1 wherein step a) of providing a polymer comprises the steps of:~~

- e) providing a polymer comprising first pendent groups which include a group according to the formula $\text{-SO}_2\text{H}$ and second pendent groups which include a group according to the formula $\text{-SO}_2\text{F}$; and

- f) converting said $\text{-SO}_2\text{H}$ groups to $\text{-SO}_2\text{Cl}$.

21. (Original) The method according to claim 14 wherein the resulting polymer has an equivalent weight of less than 1200.

22.-52. (Canceled)